


REPORT NUMBER:

NGBT06658774



TEST REPORT

Number : NGBT06658774

Applicant : SHELTA AUSTRALIA  
UNIT 4/1 FOUNDATION PLACE PEMULWUY,  
NSW, 2145, AUSTRALIA  
Attn : DAVID WILLIAMS

Date : Sep 28, 2020

Sample Description As Declared :

No. Of Sample : One  
Fibre Content : 100% Solution Dyed Polyester  
Material : Woven Fabric  
Finishing : -  
End Uses : Umbrella Canopy/Cover  
Colour : Platinum  
Style No. : B961  
Order No./PO No. : -  
Buyer's Name : Harvey Norman  
Manufacturer's Name : ACTIVA LEISURE INC.  
Ref. : -

Applicant's Provided Care Instruction/Label : -

Date Received/Date Test Started : Sep 24, 2020

Conclusion:

Determination Of Formaldehyde (Part 1)	M
Fibre Analysis	*1
Colour Fastness To Rubbing	M
Colour Fastness To Light	M
Seam Slippage As Received	M
Pilling Resistance As Received	M
Abrasion Resistance	M
Determination Of The UPF Rating Of A Dry Textile	#

Note : M = Meet Buyer's Requirement

F = Below Buyer's Requirement

# = No Specified Requirement

\* = No Submitted Information

N/A = Not Applicable

\*1 = The Fibre Label Of The Sample Shall Be Rewritten As:"100% Polyester".

Prepared And Checked By:  
Intertek Testing Service Ltd., Zhejiang, Ningbo Branch

*Winnie Pan*

Winnie Pan  
Customer Service Manager



**Intertek Testing Services Ltd., Zhejiang, Ningbo Branch**

5/F, No.6 Building, Lingyun Industry Park, 1177 Lingyun Road,  
Ningbo National Hi-Tech Zone, Ningbo, Zhejiang, 315000  
浙江天祥质量技术服务有限公司宁波分公司

浙江省宁波市国家高新区凌云路 1177 号凌云产业园 6 号楼 5 层 邮编:315000

Tel: +86 574 8818 3650 Fax: +86 574 8818 3680 E-mail: textile.ningbo@intertek.com Website: Intertek.com

Attention is drawn to the terms and conditions printed overleaf

TEST REPORT

Number : NGBT06658774

Tests Conducted (As Requested By The Applicant)

1 Determination Of Formaldehyde (Part 1) : Free And Hydrolyzed Formaldehyde (ISO 14184-1:2011):

7ppm	<u>Requirement</u> 100PPM
------	------------------------------

Remark : ppm = mg/kg

2 Fibre Analysis  
AS 2001.7-2005

<b>100% Polyester</b>	<u>Marked</u> 100% Solution Dyed Polyester
-----------------------	---

3 Colour Fastness To Rubbing (AS 2001.4.3-1995):

Dry	4-5	<u>Requirement</u> 4
Wet	4-5	3

4 Colour Fastness To Light (AS 2001.4.B02-2001, Xenon-Arc Lamp):

Grade	Above 5	<u>Requirement</u> Med & Dark 4-5
-------	---------	---

5 Seam Slippage AS Received (AS 2001.2.22-2006, Method A, Tensile Testing Machine, CRE):

(I)	The Mean Seam Opening Under 180 N Load Within 10 Seconds	<u>Requirement</u>
	// To Warp	6 mm
	// To Weft	6 mm
(II)	The Mean Seam Opening After Reducing To 2.5 N Load For 2 Minutes	
	// To Warp	6 mm
	// To Weft	6 mm

Remark : N = Newton

TEST REPORT

Number : NGBT06658774

Tests Conducted (As Requested By The Applicant)

6 Pilling Resistance As Received (ISO 12945-2:2000, Martindale Abrasion & Pilling Tester, 415 g Total Loading):

<u>After 5,000 Revolutions</u>		<u>Requirement</u>
Grade	3-4	3

7 Abrasion Resistance (AS 2001.2.25.2-2006, Martindale Abrasion And Pilling Tester, 12 kPa Total Pressure):

<u>Resistance</u>		<u>Requirement</u>
Face Side	Over 50000 Rubs	Min 15,000 Rubs

Remark: According to AS2687-1997, Modified, this sample belongs to Class 5 - Commercial Heavy Duty

The above result is the average of four test specimens. In contrary to the requirement of the standard to report individual test data herein, such data will be available upon request.

---

TEST REPORT

Number : NGBT06658774

Tests Conducted (As Requested By The Applicant)

8 Determination Of The UPF Rating Of A Dry Textile (AS/NZS 4399: 2017, Appendix A):

Solar Spectrum Irradiance Used: Noon On 17 January 1990 For Melbourne (38°S)

Number Of Specimens Tested: 4

No. Of Scans: 8

The Samples Are Tested In Dry And Relaxation State.

		<u>Requirement</u>
The Mean Ultraviolet Protection Factor, UPF:	1760.78	
Standard Deviation Of UPF:	49.89	
UPF Rating:	50+	-
UPF Classification:	Excellent	
% Of Mean UVA Transmittance (315-400 nm):	0.16%	
% Of Mean UVB Transmittance (290-315 nm):	0.05%	

TEST REPORT

Number : NGBT06658774

Tests Conducted (As Requested By The Applicant)

Determination Of The UPF Rating Of A Dry Textile (CONT'D)

Remark1:

UPF Classification System (AS/NZS 4399: 2017, Clause 5 Table 1)		
UPF	Classification	Effective UVR penetration, less than or equal to (%)
15	Minimum	6.7
30	Good	3.3
50, 50+	Excellent	2.0

Remark2: In Accordance With AS/NZS 4399:2017, A Product To Qualify For Claims Of Ultraviolet Protection Factor (UPF) Rating Only If The Product Provides Sufficient Body Surface Coverage To Offer Adequate Protection From Ultraviolet Radiation (UVR).

Besides, Each Product For Which A Claim Or Display Of A UPF Rating And Classification Against Solar UVR Is Made Shall Be Accompanied By The Specified Information, Presented In A Clear And Legible Manner By Means Of A Fixed Or Removable Label Securely Attached Or Tied To The Product At The Point Of Sale.

The Test Results Provided Herewith Is The UPF Rating Of The Fabrication Only. It Is The Manufacturer's Responsibility To Ensure The Final Product To Qualify For Claims Of UPF Rating And The Compliancy In Marking And Labeling Of The Product In Accordance With AS/NZS 4399:2017.

Note:

nm: Nanometer.

UPF: Ultraviolet Protection Factor.

---

End of Report

*Remark: This statement of conformity is only based on the actual measured test result by the laboratory, without taking the influence of uncertainty into account.*

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.*

*This report shall not be reproduced except in full, without written approval of the laboratory.*